

L-2960 Self-healing PU Resin

Description

**L-2960** is a specially modified PU resin. After cross-linking reaction with isocyanate, an interpenetrating network structure system is formed. After mixing, toughness and plasticity of base material are outstanding. After drying and film formation, scratches on the surface will not cause a fracture response, and it has good scratch resistance and quick repair effects. The paint film has the characteristics of good fullness, good aging resistance, good anti-fouling performance, and automatic repair function. It is very suitable for high-requirements automotive protective films, automotive interior parts, protective coatings for motorcycle helmets and other fields.

Technical data

Appearance	Colorless transparent liquid
Viscosity (25°C, CPS)	30 - 120
Solid content %	55±2
OH value (solid)	130mgKOH/g
OH% (solid)	3.9
Acid value (solid)	2-5mgKOH/g
Solvent	Butyl ester

Performance

The coating film has self-healing function. It can be repaired in 1 hour at room temperature and in seconds with hot water.

Good aging resistance

Good acid rain resistance and chemical resistance

Good adhesion to PVC, TPU, ABS, PC, ABS+PC and other materials

It has anti-fouling function and the water drop angle is above 105 degree

Applications

Invisible car coatings for automobiles, self-repairing coatings for motorcycles, self-repairing coatings for high-end electronic products, anti-stain coatings for various soft materials, etc.

Storage

To prevent the product from polymerization and gelling, please keep it sealed and away from heat and light. Safe storage time is 6 months at room temperature( 25°C) and under ventilation.

This product will be packed into 20KG/25KG/200KG/barrel

**Tips: L-2960's self-healing speed is slightly slower than that of L-2900. The coating film has a self-healing function and can be repaired in seconds after being heated (such as using 60°C hot water), and has anti-stain effects.**

Note: Technical data represents typical values only. In view of the differences in formulas, production process, conditions, all the above statements must be adjusted according to the actual situation, our company does not make any promises. Our company reserves the right to reform its products without prior notice of any changes.