# L-1201 High Solid Content PU Primer Resin

### **Description**

**L-1201** is an OH group-containing acrylic copolymer. When combined with non-yellowing polyisocyanate at room temperature, it can be made into a two-liquid system with good construction performance, good arrangement of silver powder, and excellent matching performance. It is very suitable for two-liquid silver paint., pearlescent powder paint, which has excellent physical and chemical properties and pigment dispersion, and can also be made into solid color paint.

1 echilical data	
Appearance	Colorless transparent liquid
Viscosity (25°C, CPS)	8,000 - 15,000
Solid content %	59±2
OH value (solid content)	60 mgKOH/g
OH % (solid content)	1.8

3-7 mgKOH/g

## Performance

Acid value (solid)

Technical data

Good adhesion to ABS, PC, PC+ fiber, PA and PA+ fiber, PMMA, fiberglass, TPU and other plastics, aluminum alloy and other metal substrates.

Good compatibility with CAB, good arrangement of silver powder, good adhesion between layers, and good pigment dispersion.

Good recoatability, especially after recoating twice and then covering with UV or PU, the adhesion is still very good after boiling.

Good chemical resistance, resistant to boiling at 100°C for 2 hours.

#### Reference formula

Aluminum paint		Thinner	
L-1201 resin	60	Xylene	45
T-12 (drier)	0.1	Ethyl acetate	20
20%CAB381-2	10	Butyl acetate	25
Aluminum silver paste	7	PMA	10
Lencolo 3108	0.3		
Adhesion promoter	1		
Thinner	21.6		

Curing agent N3390 75: Butyl ester 25 Main agent: Curing agent: Thinner =12: 1: (5~8)

#### **Applications**

Two-component PU varnish or solid color paint, flash paint for various metals and plastics, various baking paint primers, UV primers

#### Storage

To prevent the product from polymerization and gelling, please keep it sealed and away from heat and light. Recommended storage temperature is not higher than 30°C. Unused products must be sealed and stored in a timely manner and cannot be stored in the open. Safe storage time is 6 months at room temperature(25°C) and under ventilation. 20KG/25KG/200KG/barrel

# Tip: L-1201 is mainly used as a primer and has good adhesion to various metal substrates such as aluminum and stainless steel.

Note: Technical data represents typical values only. In view of the differences in formulas, production process, conditions, all the above statements must be adjusted according to the actual situation, our company does not make any promises. Our company reserves the right to reform its products without prior notice of any changes.