

L-6112D Economical UV Epoxy Resin with Low Halogen

Description

L-6112D is an epoxy acrylate resin with fast curing, good surface drying, high gloss, and high

Technical Data

Appearance	Slightly yellow, clear, transparent liquid
Viscosity (25°C, CPS)	30,000-50,000
Color Value (Gardner)	≤3
UV Content (%)	100
Density (g/cm ³ , 25°C)	1.1±0.1
Acid Value (mg KOH/g)	≤3
Refractive Index	1.525
Shore Hardness	82D
Tensile Strength (MPa)(ASTM D882)	258
Elongation at Break (%) (ASTM D882)	2.3
Functional Group	2

Product Features

High gloss
High reactivity
Fast curing and good surface drying
Good chemical resistance

Applications

UV wood coatings; UV varnishes for paper; UV plastic coatings; UV coatings for hardware, etc.

Storage Conditions

To prevent premature polymerization due to the high reactivity of this product, keep it tightly sealed and store away from heat sources and direct sunlight. It is recommended to maintain storage temperature below 30 °C. Unused product should be promptly resealed and must not be left open. Under ventilated conditions at 25 °C, the product has a safe storage period of 6 months. Available packaging: 20 kg / 200 kg drums.

Tips: L-6112D is the economical epoxy resin with the lowest halogen content.

Note: Technical data represents typical values only. In view of the differences in formulas, production process, conditions, all the above statements must be adjusted according to the actual situation, our company does not make any promises. Our company reserves the right to reform its products without prior notice of any changes.