

L-61057 (TEGDMA) Triethylene glycol dimethacrylate

CAS#: 109-16-0 C₁₄H₂₂O₆

Molecular weight (g/mol): 286.32

Description

L-61057 TEGDMA is a unique chemical structure and reactivity containing diacrylate, which is used in many polymer synthesis and light-curing systems:

In the field of optical materials, TEGDMA is mixed with other monomers such as GMA (bisphenol A dimethacrylate) and then polymerized by ultraviolet or visible light to form a hard and transparent solidified material, such as denture base resin, light-curing coating and optical fiber

In the field of polymer chemistry, TEGDMA can be used as a component of high-performance adhesives and sealants to improve the heat resistance, impact resistance and bonding strength of the product. Due to its good light transmittance and cross-linking properties, TEGDMA is also used in electronic packaging materials and potting glue to provide excellent electrical insulation and

In light-curing 3D printing technology, TEGDMA, as part of the resin formula, can adjust the fluidity and curing speed of the resin, thereby affecting the printing accuracy and mechanical properties of the final product. In addition, TEGDMA may also play a role in the preparation of other materials that require rapid curing, such as the production of wear-resistant coatings, anti-slip layers, decorative layers, etc.

Technical Data

Appearance	Transparent liquid
Color Value (APHA)	≤ 60
Acid Value (mg)	≤ 0.5
Viscosity (25°C, CPS)	5-15
Moisture %	≤ 0.2
Inhibitor (ppm)	≤ 300
Refractive Index	1.458
Surface Tension Dynes/cm, 20°C	34.8
Glass Transition Temperature T _g , °C	53
Functional Group	2

Product Features

Low irritation, good hardness and toughness
Good heat resistance, high chemical resistance
High cross-linking density, good hydrophobicity
Very low volatility, good dilution

Applications

UV adhesives; UV inkjet; UV ink; UV coatings; UV hydrophobic coatings; photosensitive polymers; wire and cable coatings; adhesives and sealants; excellent compatibility with unsaturated polyesters used for chemical fixing and anchor bolts

Storage Conditions

To prevent premature polymerization due to the high reactivity of this product, keep it tightly sealed and store away from heat sources and direct sunlight. It is recommended to maintain storage temperature below 30 °C. Unused product should be promptly resealed and must not be left open. Under ventilated conditions at 25 °C, the product has a safe storage period of 6 months. Available packaging: 25 kg / 200 kg per drum

Tips: L-61057 is an ideal product for the formulation of dibenzoyl peroxide (BPO) curing system, with excellent active dilution ability and stability.

Note: Technical data represents typical values only. In view of the differences in formulas, production process, conditions, all the above statements must be adjusted according to the actual situation, our company does not make any promises. Our company reserves the right to reform its products without prior notice of any changes.