

SQ-720508 One-component Primer

Description

SQ-720508 one-component primer has good adhesion to plastic substrates such as ABS, PC, PVC, etc., good silver row effect, excellent metallic texture, fast curing speed and good interlayer adhesion.

Technical data

Viscosity (Yantian No. 2 cup)	50±0.2s
Chroma (Gardner)	≤1
Solid content%	21±2%
Acid value (mg KOH/g)	≤3
Pencil hardness	HB

Performance

Excellent adhesion to plastic substrates such as ABS, PC, PVC, etc.

Fast curing speed, good interlayer adhesion

Good silver row effect, excellent metal texture

Applications

Recommended for plastic spraying, 3C product spraying, and imitation electroplating spraying.

Usage guide

Sample original viscosity: 68s

Solid content: 70%

Recommended thinner:

EAC 40%

BAC 20%

IBA 40%

Recommended thinning ratio: 1 : 1.03 (9.06s)

Recommended silver powder addition ratio: 5-7%

Storage

To prevent the product from polymerizing and gelling, please seal it and store it away from heat sources and sunlight. Under normal circumstances, the safe storage period is 6 months.

20KG/200KG/barrel

Note: Technical data represents typical values only. In view of the differences in formulas, production process, conditions, all the above statements must be adjusted according to the actual situation, our company does not make any promises. Our company reserves the right to reform its products without prior notice of any changes.